

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 September 2002 (06.09.2002)

PCT

(10) International Publication Number
WO 02/068352 A2

- (51) International Patent Classification⁷: C03C
- (21) International Application Number: PCT/GB02/00684
- (22) International Filing Date: 18 February 2002 (18.02.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0104347.0 22 February 2001 (22.02.2001) GB
- (71) Applicant (for all designated States except MN, US):
RECKITT BENCKISER N.V. [NL/NL]; Kantoorgebouw de Appelaer, De Fruittuinen 2-12, NL-2132 NZ Hoofddorp (NL).
- (71) Applicant (for MN only): RECKITT BENCKISER (UK) LIMITED [GB/GB]; 103-105 Bath Road, Slough, Berkshire SL1 3UH (GB).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): HAHN, Karlheinz, Ulrich, Gerhard [DE/DE]; Friedhofstrasse 13, 67166 Otterstadt (DE).
- (74) Agents: BROWN, Andrew, Stephen et al.; Reckitt Benckiser plc, Group Patents Department, Dansom Lane, Hull, HU8 7DS (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: WATER-SOLUBLE GLASS AS CORROSION PROTECTOR IN DISHWASHING MACHINES

(57) Abstract: A zinc-containing, water-soluble glass composition comprising from 41 to 54 mole % of P₂O₅, 10 to 30 mole % of alkali oxides, up to 5 mole % of SO₃ and up to 25 mole % of ZnO.

WO 02/068352 A2

5

Water-soluble glass as corrosion protector in dishwashing machines

The invention is related to a novel zinc-containing, water-soluble glass composition, the use thereof for inhibition of corrosion of glassware in an automatic dishwashing process and related processes.

10

Corrosion of glassware in cleaning and/or rinsing cycles of an automatic dishwashing machine is a well-known problem. It is believed that corrosion of glassware can be seen as two separate phenomena. On the one hand, corrosion is obviously caused by the leakage of minerals from the glass composition, accompanied by the hydrolysis of the silicate network. On the other hand, deposition of silicate material on the glassware may take place. Those phenomena will result, after a certain number of cleaning cycles, to damages on the glassware, such as turbidity, scratches, streaks and the like.

15

It is known that silicate compounds could be active against leakage of minerals from glass compositions. However, deposition of silicate material on the surface of glassware would be increased.

20

There are different approaches in the prior art proposed for the solution of above identified problems.

One approach is the use of zinc, either in metallic form (U.S. Patent No. 3,677,820) or in the form of zinc compounds. The use of soluble zinc salts for inhibition of corrosion of glassware in automatic dishwashing processes is, for example, disclosed in U.S. Patent No. 3,255,117.

25

There are, however, various disadvantages of the use of soluble zinc salts, in particular formation of precipitates of insoluble zinc salts with other ions in the wash liquor or rinse water. Thus, the use of insoluble zinc compounds for the inhibition of corrosion of glassware in automatic dishwashing processes has been proposed in European Patent Application EP 0 383 480 A1, EP 0 383 482 A1 and EP 0 387 997 A1. More particularly insoluble zinc salts such as zinc silicate, zinc carbonate, zinc oxide, basic zinc carbonate, zinc hydroxide, zinc oxalate, zinc

30

monophosphate and zinc pyrophosphate have been proposed.

2 -

- 5 With these prior art compositions, it is disadvantageous that, due to the low solubility, or even insolubility, of the zinc compounds, it is difficult, if not impossible, to ensure an continuously sufficient amount of active corrosion inhibiting agent in the wash liquor or rinse water. Moreover, due to the high specific density of above mentioned insoluble zinc salts, separation problems of powder mixtures or deposition problems with liquid mixtures have occurred.
- 10 WO 97/11151 discloses glassy particles containing agents useful for laundry and cleaning products. Amongst others, material care agents are disclosed such as usual corrosion inhibitors such as paraffin oil, benzotriazole, and the like. The agents are encapsulated in glassy particles derived from at least partially water-soluble hydroxylic compounds such as sucrose, glucose and maltodextrin. No zinc-containing water-soluble glass compositions are disclosed therein.
- 15 WO 00/39259 discloses the use of water-soluble glasses as corrosion protection for glassware. This water-soluble glass composition comprises at least one compound, which in cleaning and/or rinsing cycles of a dishwashing machine releases a corrosion inhibiting agent. The solubility of the glass is defined by a mass loss of at least 0.5 mg under specified conditions. Amongst others, zinc-containing glasses are disclosed. In preferred embodiments, the glass building component is
- 20 preferably phosphorous pentoxide and additionally comprises at least one alkali oxide. The examples disclosed therein are characterised by a content of SO_3 of around 20 %.

However, the glass composition disclosed in WO 00/39259 which is based on ZnO (which is presently believed to be a very effective glassware-protecting agent) turned out to be unsatisfactory for manufacture of a consumer appealing product. In fact, although it is possible,

25 under certain conditions, to manufacture a transparent glass from the composition, this glass loses its transparency rapidly after some dishwashing cycles developing an unappealing appearance.

Related compositions obtained by variation of the components resulted in problems of producing a transparent glass in a continuous manufacturing process, which is required for production of

30 large amounts of the glass product. In such processes, the raw materials for glasses are molten in a furnace at temperatures where they form a liquid glass melt with viscosities from 1 to 1000 dPas (100 dPas characterises the well know "Melting Point") Afterwards the melt is continuously slowly cooled down and remains during a long period working temperature range where it shows a viscosity of 10^4 to 10^8 dPas. This is called the processing range of glass, determined by the

35 "Working Point", where the liquid glass shows a viscosity of 10^4 dPas and the "Littleton Point",

5 $10^{7.6}$ dPas, where the shape of glass is formed by pressing or/and blowing. Finally, the composition reaches the glass transition temperature range (T_g) where its viscosity increases becoming a solid material. In this range ("Annealing Point", viscosity of 10^{13} dPas and "Strain Point" $10^{14.6}$ dPas) tensions could be minimised due to annealing.

10 The time during which the glass remains within the working temperature range facilitates devitrification of the glass formulation. In non-continuous processes (such as those employed in the manufacture of optical glasses or glasses used as fillers for plastics), the glass is quickly cooled down after it comes out of the furnace and therefore devitrification does usually not occur. The formulation of the glass is, however, much more critical, when manufacturing transparent glasses in a continuous process with above described prolonged cooling down periods.

15 Thus, it is an object of the present invention to provide for a zinc-containing, water-soluble glass composition for use as a corrosion inhibiting product in an automatic dishwashing process which allows production of transparent glass in a continuous manufacturing process which glass maintains its transparency upon dissolution over a sufficient number of dishwashing cycles.

20 This object is solved by a zinc-containing, water-soluble glass composition comprising from 41 to 54 mole % of P_2O_5 , 10 to 30 mole % of alkali oxides, up to 5 mole % of SO_3 and up to 25 mole % of ZnO .

25 In a preferred embodiment of the inventive glass composition not more than 40 mole %, preferably not more than 20 mole %, most preferably not more than 10 mole % of the total amount of alkali oxides in the glass formulation is constituted by one or more members of the group consisting of Li_2O and Na_2O .

Preferably, the inventive composition additionally comprises at least one alkaline-earth oxide with a total amount of alkaline-earth oxides of less than 20 mole %, preferably less than 10 mole % and, most preferably less than 5 mole %.

30 Also preferably, the inventive composition additionally comprises at least one oxide of antimony or arsenic with a total amount of such oxides of less than 5 mole %, preferably less than 3 mole %, most preferably less than 1 mole %.

4 -

- 5 The inventive composition may comprise oxides of an element from the group consisting of silicon, germanium, tin and lead with a total amount of such oxides of less than 10 mole %, preferably less than 5 mole %, most preferably less than 3 mole %, wherein no single of such oxides is present in an amount exceeding 5 mole %, more preferably 2 mole %.

- 10 Even more preferably, the inventive composition additionally comprises at least one oxide of an element selected from the group consisting of aluminium and boron with a total amount of such oxides of from 0.1 to 10 mole %, preferably from 0.2 to 5 mole %, most preferably from 0.3 to 3 mole %.

- 15 It is also preferred that the glass compositions according to the present invention do not comprise more than 0.5 mole % of oxides of elements from the group IIIb of the Periodic System of Elements (i.e. the group comprising Scandium, Yttrium, the Lanthanide series and the Actinide series).

- 20 The presently most preferred composition according to the invention consists of from 41 to 54 mole % of P_2O_5 , from 10 to 30 mole % of alkali oxides, up to 5 mole % of SO_3 , up to 25 mole % of ZnO, less than 5 mole % of alkaline-earth oxides, and from 0.3 to 3 mole % of oxides of elements selected from the group consisting of silicon, aluminium and boron.

In the most preferred embodiment of the invention, the composition is present in the form of a transparent shaped body, preferably manufactured by continuous glass manufacturing processes like casting, pressing or blowing.

- 25 In an alternative, the composition is present in a comminuted form, preferably either manufactured by breaking of thin glass plates or by milling, wherein the milled glass most preferably has an average particle size of not more than 500 microns.

The invention is specifically related to the use of the inventive glass composition for inhibition of corrosion of glassware in an automatic dishwashing process, particularly to the use of a transparent glass composition, which remains transparent upon dissolution.

- 30 Thus, the invention is also related to processes for inhibition of corrosion of glassware in an automatic dishwashing process, either characterised by contacting the glassware, in an automatic

5 -

- 5 dishwashing machine, with wash liquor and/or rinse water containing an effective amount of the inventive composition, or by providing the composition, in particular in the form of a shaped body, such as a glass block drop casted and pressed in a continuous manufacturing process, at an appropriate place within an automatic dishwashing machine being accessible for the wash liquor and/or rinse water.
- 10 Very surprisingly, only the specific selection of components in their indicated ranges simultaneously fulfils the requirements of releasing ZnO during the dishwashing cycles in an amount enough to ensure glassware corrosion protection, providing for a dissolution rate of the glass enabling to use a block of reasonable weight for a reasonable number of washing cycles (for example, 40 g for 60 cycles), and allowing manufacture of a transparent glass block in an
- 15 continuous manufacturing process which glass block does not loose its transparency during a sufficient number of dishwashing cycles.

Although a multitude of glass formulations is known from the prior art, we are presently not aware of any such composition with this specific choice of components in the specified ranges. In particular, above mentioned advantageous features enabling the desired use of the glass

20 composition for manufacturing a consumer appealing glass product for inhibition of corrosion of glassware in automatic dishwashing has neither been anticipated nor obvious for someone skilled in the art from the prior art documents related to glass formulations.

The compositions as exemplified in the following Table have been produced in a continuous commercial glass pressing processing as outlined hereinabove. It is easily possible to

25 manufacture shaped bodies of transparent glass with a weight of about 40 g. When used in an automatic dishwashing machine, the glass block was completely dissolved after several dishwashing cycles. For example 1 a glass block with the dimensions (1 x 5 x 3) cm³ was completely dissolved after 60 cycles in the dishwasher, if you choose the conditions described in prEN 12875-1 with Calgonit Powerball Tab as detergent. No loss of transparency of the glass

30 block was observed over this time period.

The glass corrosion inhibiting activity of these glass blocks were tested according the methods as described in detail in WO 00/39259. The results were found to be at least equal, in case of the composition according to Example 1 even significantly better.

6 -

5

Table

Component	Exp. 1 [mole %]	Exp. 2 [mole %]	Exp. 3 [mole %]
P ₂ O ₅	50	45	43
Na ₂ O	1	0	0
Li ₂ O	0	3	0
K ₂ O	27.5	25	29
ZnO	14.5	15	19
CaO	3	5	0
SO ₃	0	4,5	3
Sb ₂ O ₃	0	0.5	0
SiO ₂	2	0	3
Al ₂ O ₃	0.5	0	1
B ₂ O ₃	1.5	2	2
Total	100	100	100

The features disclosed in the foregoing description, and the claims may, both separately and in any combination thereof, be material for realising the invention in diverse forms thereof.

5 Claims

1. A zinc-containing, water-soluble glass composition comprising from 41 to 54 mole % of P_2O_5 , 10 to 30 mole % of alkali oxides, up to 5 mole % of SO_3 and up to 25 mole % of ZnO .
2. The composition according to claim 1 characterised in that not more than 40 mole %, preferably not more than 20 mole %, most preferably not more than 10 mole % of the total amount of alkali oxides in the glass formulation is constituted by one or more members of the group consisting of Li_2O and Na_2O .
3. The composition according to claim 1 or claim 2 characterised in that it additionally comprises at least one alkaline-earth oxide with a total amount of alkaline-earth oxides of less than 20 mole %, preferably less than 10 mole %, most preferably less than 5 mole %.
- 15 4. The composition according to any of the preceding claims characterised in that it additionally comprises at least one oxide of antimony or arsenic with a total amount of such oxides of less than 5 mole %, preferably less than 3 mole %, most preferably less than 1 mole %.
5. The composition according to any of the preceding claims characterised in that it additionally comprises at least one oxide of an element from the group consisting of silicium, germanium, tin and lead with a total amount of such oxides of less than 10 mole %, preferably less than 5 mole %, most preferably less than 3 mole %, wherein no single of such oxides is present in an amount exceeding 5 mole %, more preferably 2 mole %.
- 20 6. The composition according to any of the preceding claims characterised in that it additionally comprises at least one oxide of an element selected from the group consisting of silicon, aluminium and boron with a total amount of such oxides of from 0.1 to 10 mole %, preferably from 0.3 to 5 mole %, most preferably from 0.3 to 3 mole % of oxides of elements.
- 25 7. The composition according to any of the preceding claims characterised in that it does not comprise more than 0.5 mole-% of oxides of elements from the group IIIB of the Periodic System of Elements.
- 30

- 5 8. The composition according to any of the preceding claims characterised in that it consists of from 41 to 54 mole % of P_2O_5 , from 10 to 30 mole % of alkali oxides, up to 5 mole % of SO_3 , up to 25 mole % of ZnO , less than 5 mole % alkaline-earth oxides, and from 0.3 to 3 mole % of oxides of elements selected from the group consisting of silicon, aluminium and boron.
- 10 9. The composition according to any of the preceding claims characterised in that it is present in the form of a transparent shaped body.
10. The composition according to claim 9 characterised in that the shaped body is manufactured by continuous glass manufacturing processes like casting, pressing or blowing.
11. The composition according to any of claims 1 to 8 characterised in that it is present in a
15 comminuted form.
12. The composition according to claim 11 characterised in that the composition is manufactured by breaking of thin glass plates.
13. The composition according to claim 11 characterised in that the composition is manufactured by milling.
- 20 14. The composition according to claim 13, characterised in that the milled glass has an average particle size of not more than 500 microns.
15. Use of a zinc-containing, water-soluble glass composition according to any of the preceding claims for inhibition of corrosion of glassware in an automatic dishwashing process.
- 25 16. Process for inhibition of corrosion of glassware in an automatic dishwashing process characterised by providing a composition according to any of claims 1 to 14, in particular in the form as claimed in claims 9 and 10, at an appropriate place within an automatic dishwashing machine being accessible for the wash liquor and/or rinse water.

- 5 17. Process for inhibition of corrosion of glassware in an automatic dishwashing process characterised by contacting the glassware, in an automatic dishwashing machine, with wash liquor and/or rinse water containing an effective amount of a composition according to any of claims 1 to 14, in particular in the form as claimed in claims 11 to 14.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 September 2002 (06.09.2002)

PCT

(10) International Publication Number
WO 2002/068352 A3

- (51) International Patent Classification⁷: C03C 3/066, 3/16, 3/19, C11D 3/06, 3/08
- (21) International Application Number: PCT/GB2002/000684
- (22) International Filing Date: 18 February 2002 (18.02.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 0104347.0 22 February 2001 (22.02.2001) GB
- (71) Applicant (for all designated States except MN, US): RECKITT BENCKISER N.V. [NL/NL]; Kantoorgebouw de Appelaer, De Fruittuinen 2-12, NL-2132 NZ Hoofddorp (NL).
- (71) Applicant (for MN only): RECKITT BENCKISER (UK) LIMITED [GB/GB]; 103-105 Bath Road, Slough, Berkshire SL1 3UH (GB).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): HAHN, Karlheinz, Ulrich, Gerhard [DE/DE]; Friedhofstrasse 13, 67166 Otterstadt (DE).
- (74) Agents: BROWN, Andrew, Stephen et al.; Reckitt Benckiser plc, Group Patents Department, Dansom Lahe, Hull, HU8 7DS (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- (88) Date of publication of the international search report: 31 December 2003
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: WATER-SOLUBLE GLASS AS CORROSION PROTECTOR IN DISHWASHING MACHINES

(57) Abstract: A zinc-containing, water-soluble glass composition comprising from 41 to 54 mole % of P₂O₅, 10 to 30 mole % of alkali oxides, up to 5 mole % of SO₃ and up to 25 mole % of ZnO.

WO 2002/068352 A3

INTERNATIONAL SEARCH REPORT

PCT/GB 02/00684

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C03C3/066 C03C3/16 C03C3/19 C11D3/06 C11D3/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C03C C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	EP 1 116 698 A (ISHIZUKA GLASS) 18 July 2001 (2001-07-18) example C; table 1	1-17
Y	US 3 589 858 A (RALSTON PAUL H) 29 June 1971 (1971-06-29) the whole document	1-17
Y	US 2 337 856 A (OWEN RICE ET AL) 28 December 1943 (1943-12-28) page 3, right-hand column, line 49	1-17
Y	WO 00 39259 A (HAHN KARLHEINZ ; RECKITT BENCKISER NV (NL)) 6 July 2000 (2000-07-06) cited in the application tables 1,5	1-17

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the International filing date but later than the priority date claimed

- *T* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *S* document member of the same patent family

Date of the actual completion of the international search

12 June 2002

Date of mailing of the international search report

21/06/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Somann, K

INTERNATIONAL SEARCH REPORT

Information on patent family members

PCT/GB 02/00684

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1116698	A	18-07-2001	JP 2001247333 A	11-09-2001
			AU 7252000 A	05-07-2001
			EP 1116698 A1	18-07-2001
			US 2001023156 A1	20-09-2001
US 3589858	A	29-06-1971	GB 1155113 A	18-06-1969
US 2337856	A	28-12-1943	NONE	
WO 0039259	A	06-07-2000	DE 19860670 A1	10-08-2000
			AU 2286900 A	31-07-2000
			WO 0039259 A1	06-07-2000
			EP 1141190 A1	10-10-2001